



Cadillac Products Packaging Company

PRODUCT INFORMATION BULLETIN

CADPAK S Series

QPL MIL-PRF-131K

Barrier Material: Watervaporproof, Greaseproof, Flexible, Heat-Sealable, Class 3, Type 1

Structure description: PolyCotton-Scrim/PE/Foil/PE

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUES	UNITS	TEST METHOD
Caliper	13.3	mil	ASTM D2103
Yield	3,270	in ² /lb	Calculated
Puncture Resistance	>22	lbs	MIL STD 3010
Tensile Strength	53	lbs	ASTM D882
OTR	0.0005	cc/100 in ² /day @0% RH, 23°C	ASTM D3985
WVTR	0.0005	g/100 in ² /day @ 90% RH 40°C	ASTM F1249
Seal Strength	10	lb/in	ASTM F88
Suggested Sealing Conditions	435°F, 60psi, 3.0sec		

01/30/08:1002-S

The information on this data sheet has been established by company based laboratory testing. This information does not imply warranty by Cadillac Products Packaging Co. for product specifications, tolerances, or function in the end use.

This document is confidential and may be legally privileged. If you are not an intended recipient or an authorized representative of an intended recipient, you are prohibited from using, copying or distributing the information in this document.