



Cadillac Products Packaging Company

## PRODUCT INFORMATION BULLETIN

# **CADPAK VCI/Ferro Film XP**

QPL MIL-PRF22019D

### Structure description: OPP/PE/VCI Sealant

#### PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUES	UNITS	TEST METHOD
Caliper	4.5	mil	ASTM D2103
Yield	7,450	in <sup>2</sup> /lb	Calculated
Puncture Resistance	20	lbs	FED STD 101
Tensile Strength	MD-30 TD-45	lbs/in	ASTM D882
OTR	100.0	cc/100 in <sup>2</sup> /day @0% RH, 23°C	ASTM D3985
WVTR	0.19	g/100in <sup>2</sup> /day @ 90% RH 40°C	ASTM F1249
Seal Strength	10	lbs/in	ASTM F88
Suggested Sealing Conditions	375°F, 40psi, 1.0sec		Range 275°-400°F

04/10/08:5564-PP-PE-VCI

The information on this data sheet has been established by company based laboratory testing. This information does not imply warranty by Cadillac Products Packaging Co. for product specifications, tolerances, or function in the end use.

This document is confidential and may be legally privileged. If you are not an intended recipient or an authorized representative of an intended recipient, you are prohibited from using, copying or distributing the information in this document.