



Cadillac Products Packaging Company

PRODUCT INFORMATION BULLETIN

CADPAK CL II

TRANSPARENT HIGH BARRIER PACKAGING

QPL MIL-PRF-22191F, Type II, Class 2

Barrier Material: Waterproof, Greaseproof, Flexible, Heat Sealable

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUES	UNITS	TEST METHOD
Caliper	3.2	mil	ASTM D2103
Yield	8,590	in ² /lb	Calculated
Puncture Resistance	19	lbs	Mil-Std-3010
Tensile Strength MD/TD	20/20	lbs/in	ASTM D882
OTR	0.12	cc/100 in ² /day @0% RH, 23°C	ASTM D3985
WVTR	0.39	g/100 in ² /day @ 90% RH 40°C	ASTM F1249
Seal Strength	16	lbs/in	ASTM F88
Suggested Sealing Conditions	350°F, 40psi, 1.0sec		

10/07/14:5335-CLII

The information on this data sheet has been established by company based laboratory testing. This information does not imply warranty by Cadillac Products Packaging Co. for product specifications, tolerances, or function in the end use.

This document is confidential and may be legally privileged. If you are not an intended recipient or an authorized representative of an intended recipient, you are prohibited from using, copying or distributing the information in this document.